

# Forest-Multiply AS Gum® Birch



Technical board composed of a phenolic plywood core 100% birch covered on one side with anti-slip SBR gum with pyramid pattern.

**Gluing**  
Class III (EN 314-2)

**Colour**  
Black  
Light grey

**Reverse**  
Phenolic film  
Aluminium  
HPL

**Main uses**  
High security floors



Thickness (mm)	Dimensions (mm)
From 6 until 125	From 2440 *1220 until 4000*1500

**Characteristics** (only related to the birch plywood board in the standard configuration)

	Unit	Values	Standards
Density	Kg/m <sup>3</sup>	650 ± 50	UNE-EN 323
Elasticity unit	Longitudinal	>9.500 MPa	UNE-EN 310
	Transverse	>8.200 MPa	UNE-EN 310
Resistance to elasticity	Longitudinal	>90 MPa	UNE-EN 310
	Transverse	>78 MPa	UNE-EN 310
Formaldehyde emissions		E1	EN 717-2
		CARB Phase 1 <sup>§</sup>	
		CARB Phase 2 <sup>§</sup>	93120
Resistance to unstuck	MPa	96,5	UNE-EN ISO 178
Absorption of water at 20°	%	2,31	UNE-EN ISO 62
Resistance to unstuck by traction	N	2330	ASTm C 297
Reaction to fire		D-S2,d0	UNE 13501-1
Resistance to uprooting screws	daN	198	UNE-EN 13446
Acoustic isolation	dBA	27,1 ± 1,0	UNE-EN ISO 140-3
Determination of combustion heat	Mj/Kg	18,24	UNE-EN ISO 1716

\* Indicated data are based on tests realised in independent laboratories.  
\* These data are based on core and sheets specific thickness, therefore it may be interpreted as guidance.  
§ Only under special requirements.